

# FKM ELAFTOR 3061



**Manufacturer:**  
"HaloPolymer Kirovo-Chepetsk", LLC

**Synonyms:** FKM246  
**Chemical composition:** VDF+HFP+ TFE  
**Cure type:** Bisphenol, amine  
**HS code:** 3904692000  
**CAS Number:** 25190-89-0

ELAFTOR 3061 is a bisphenolic and diamine cured fluoroelastomer which is a terpolymer of VDF+HFP+TFE. ELAFTOR 3061 operating temperature range is from -15° to 250°C (from 5° to 482°F). The product is processed by compression molding.



### Parameters of raw gum\*:

PROPERTIES	UNITS	TYPICAL VALUE	TEST METHOD
<b>Appearance</b>	-	Sheets or lumps of agglutinated crumbs	-
<b>Mooney viscosity, ML 1+10 @ 121°C / 250°F</b>	MU	65	ISO 289-1
<b>Volatile loss</b>	% wt. max	0,5	ISO 248 (120°C / 248°F)
<b>Fluorine content</b>	% wt.	68	Potentiometric
<b>Specific gravity</b>	g/sm <sup>3</sup>	1,87	ISO 2781, ASTM 792
<b>T glass transition</b>	°C	-13	ISO 22768

\* These are typical properties and are not to be used for specification purpose.

### Parameters of cured gum\*:

**press cure** 30min @ 170°C / 338°F

PROPERTIES	UNITS	TYPICAL VALUE	TEST METHOD
<b>Tensile strength</b>	MPa	14,5	ISO 37
<b>Elongation</b>	%	220	ISO 37
<b>Compression set</b>	%	29	ISO 815 (70h @ 200°C / 392°F disc)
<b>Hardness</b>	Shore A	74	ISO 48-4

\*Properties of cured rubber are not to be used for specification purpose.

# FKM ELAFTOR 3061

## Compound Formulation:

FORMULATION	UNITS	TYPICAL VALUE
Rubber	Phr	100
Ca(OH) <sub>2</sub>	Phr	6
MgO	Phr	3
N-990MT Carbon Black	Phr	30
VC-50	Phr	3
VC-20	Phr	1



### Main application:

Elaftor 3061 is an excellent choice for making low permeation fuel hoses, tubes and other extrusion products.



### Package:

ELAFTOR 3061 is available in 22kg box



### Safety and Handling:

- Handle in well-ventilated areas;
- Fumes must not be inhaled;
- Eye and skin contact must be avoided. In case of skin and eye contact wash with water immediately and seek medical help;
- Smoking is prohibited;
- Do not use metallic particulate as mixing agent as it can decompose at high temperature;
- Store away from heat, keep in clean and dry area.

**Before using fluoroelastomer please read the Material Safety Data Sheet carefully.**